

Nero

— BLEND



1000x3000 mm / 39.4”x118.1”



- 1000x3000 mm
- 1000x1000 mm
- 1000x3000 mm ♦
- Laminam 3+ | Laminam 5
- Laminam 5
- Laminam 3

Coefficient of friction: Laminam 5 / Laminam 5+

Coefficiente d'attrito | Coefficient de frottement | Reibungskoeffizient | Coeficiente de fricción |

Norm-Method	1000x3000 mm
Norma-Metodo Norme-Méthode Norm-Methode Norma-Metodo	1000x1000 mm
DIN 51130	R9
DIN 51097	A
ANSI A137.1 (DCOF)	≥ 0,42*

* Guaranteed if requested at the time of ordering | Garantito su richiesta in fase d'ordine |
Garanti sur demande au moment de la commande | auf Anfrage in der Bestellphase garantier | Garantizado por encargo durante la fase de pedido

Pendulum

Norm-Method		
Norma-Metodo Norme-Méthode Norm-Methode Norma-Metodo		
Spanish test	UNE-ENV 12633:2003	on demand
English test	BS 7976-2:2002 PENDULUM TEST	on demand
Australian test	AS/NZS 4586	on demand

♦ FULL SIZE
Untrimmed end product. | Lastra formata "uscita forno" quindi non rifilata. |
Produit fini non coupe | Plattenformat nicht rektifiziert | Tabla formata "salida de horno" y, por lo tanto, no recortada.

Pictures colours and features have to be considered indicative. | I toni e le caratteristiche delle immagini sono da considerarsi indicativi | Les teintes et les caractéristiques des images sont uniquement à titre indicatif | Die gezeigten Farben und Muster sind zünftig und nicht verbindlich | Los tonos y las características de las imágenes deben considerarse solamente indicativas